



DRY READY-MIX PRODUCT
**BASEMENT SEALER
 HYDRAULIC CEMENT™**
 WATERPROOFING
 FAST SETTING HYDRAULIC MORTAR

COMMERCIAL
 GRADE

**PRODUCT
 DATA**
#5867

04/01/20
superseding: 03/03/20

PRODUCT DESCRIPTION:

BASEMENT SEALER HYDRAULIC CEMENT™ is a fast setting waterproofing mortar. It sets in 3-5 minutes to stop active leaks, even under pressure. Seals open joints and very large cracks in masonry walls and floor and wall joints.

- Fast setting hydraulic mortar
- Sets in 3-5 minutes
- Stops water, even under pressure
- Patch mortar joints, cracks and holes in masonry walls
- No top-coat required

BASEMENT SEALER HYDRAULIC CEMENT™ USES:

BASEMENT SEALER HYDRAULIC CEMENT™ Anchors metal to concrete. Ideal for sealing floor and wall joints and settlement cracks in masonry walls and swimming pools. This fast-setting hydraulic mortar patches holes even where water is actively flowing through them.

SURFACE PREPARATION:

Wear eye protection, rubber gloves and a dust mask. The area to be patched should be cleaned thoroughly by wire brushing, scraping or any other effective process.

Back chisel out the area to be patched to the shape of an inverted "V" (the point at the surface). This allows the patch to expand and lock into the surface. Wet down the area prior to patching to help the **BASEMENT SEALER HYDRAULIC CEMENT™** cure properly. **BASEMENT SEALER HYDRAULIC CEMENT™** and clean mixing water should be at room temperature prior to mixing. Mix 3 parts Ultra Plug and 1 part water thoroughly to a putty or heavy troweling consistency. This mixture will set in 3-5 minutes. The use of colder water will retard the setting time. Mix only enough for immediate use due to the quick setting time. **BASEMENT SEALER HYDRAULIC CEMENT™** cannot be reworked once it has set. In cold weather, use warm (90°F.) water for mixing; also soak surface with warm water before application.

APPLICATION PROCEDURE:

BASEMENT SEALER HYDRAULIC CEMENT™ and clean mixing water should be at room temperature prior to mixing. Mix 3 parts Ultra Plug and 1 part water thoroughly to a putty or heavy troweling consistency. This mixture will set in 3-5 minutes. The use of colder water will retard the setting time. Mix only enough for immediate use due to the quick setting time. **BASEMENT SEALER HYDRAULIC CEMENT™** cannot be reworked once it has set. In cold weather, use warm (90°F.) water for mixing; also soak surface with warm water before application. Mix only enough for immediate use, because **BASEMENT SEALER HYDRAULIC CEMENT™** sets in 3-5 minutes.

Cannot be reworked once it has set. Mix in small batches only. Mix only enough for use in 3 minutes. Discard all left over mixed patching material prior to starting a new batch. Left over patching material will chemically react with new material in the mixing receptacle.

For Active Leaks (the presence of flowing water through a break in the surface): Mix appropriate amount of **BASEMENT SEALER HYDRAULIC CEMENT™**. In approximately 2 1/2 - 3 minutes, the mixture will become warm to the touch which indicates it is commencing to set. At this time force the **BASEMENT SEALER HYDRAULIC CEMENT™** into the opening with the palm of the hand. Hold in place for 3-5 minutes, assuring a complete set and sufficient bond to stop the flow of water. The patched area may be smoothed and trimmed to the surrounding area in approximately 5 minutes. **BASEMENT SEALER HYDRAULIC CEMENT™** may be painted when set with **BASEMENT SEALER™** or **BASEMENT SEALER PLUS™** or **BASEMENT SEALER CLEAR™**.

For Inactive Leaks, Patching, Anchoring: Thoroughly soak the area to be patched. This will prevent the surface from sucking the water out of the patching material. Apply with knife or trowel. Use the surface to smooth the patch evenly. When anchoring, chisel or drill hole in the masonry surface slightly larger than item to be anchored. Make certain mixed **BASEMENT SEALER HYDRAULIC CEMENT™** is tamped firmly into hole and around metal part.

CLEAN UP:

Clean up with Soap and water. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.

Concrete

Specialty

Ambient Temperature of 77°F and RH of 50%

TECHNICAL SPECIFICATIONS:

Rates & Times May Vary Beyond Specifications

FINISH:	Cement	SPREAD RATE:	16 cu. in. per pound
COLOR (Tintable):	Gray-ready Mix Formula	DRY to TOUCH:	3-5 Minutes
VEHICLE TYPE:	N/A	RECOAT:	12 Hours
SOLIDS by WEIGHT:	100%	SET TIME:	3-5 Minutes
SOLIDS by VOLUME:	100%	SIZES:	50 Pound Bucket
V.O.C.'s (averages):	N/A	GALLON WEIGHT:	24 Pounds +/- .5%

Information presented on this Data Sheet has been compiled from sources to be reliable, and is accurate and reliable to the best of our knowledge and belief but is not guaranteed to be so.

In Any Event Nationwide Protective Coating Manufacturers, Inc. will not be liable or responsible for any past, present or future leaks or any resulting consequential or incidental damages.