



ACRYLIC CERAMIC – LOW ODOR
ENVIRO-3000®
GREEN TECHNOLOGY - ZERO V.O.C.
INTERIOR PRIMER and SEALER

PRODUCT DATA
#1090
03/26/10
superseding: 04/24/09

PRODUCT DESCRIPTION:

ENVIRO-3000® Primer Sealer is a low odor, Zero V.O.C.* (Volatile Organic Compound), high quality, insulating ceramic, interior wall, ceiling and trim, primer sealer. It is formulated with ceramic fillers, that provide insulating and soundproofing characteristics along with a uniform, easy to apply, flat priming finish. A high concentration of resin allows this Primer Sealer to seal most water, grease, oil, and other stains. It's performance stems from the high quantity of resin which provides for outstanding bonding, priming and sealing of most any interior surface. ENVIRO-3000® Primer Sealer will seal most stains, but if stains persist, a compatible stain blocker must be used. When applied according to specifications, ENVIRO-3000® paint products offer a 20 YEAR LIMITED MATERIAL WARRANTY.

** This paint is described as "Zero V.O.C." because it doesn't contain any of the solvents that are normally used in conventional latex paints. Trace amounts of V.O.C.s may be present as residual components of other ingredients. Adding Colorant to this product will add V.O.C.s, although the total V.O.C. content will still be negligible.*

ENVIRO-3000® PRIMER SEALER USES:

ENVIRO-3000® can be used on most wall, ceiling & trim surfaces such as plaster, wallboard, wood, concrete, brick, masonry, non-ferrous metal, primed ferrous metal, well bonded wallpaper and various other substrates. ENVIRO-3000® is excellent for most residential, commercial and industrial applications.

STAINS:

Spot prime all stains before priming entire area. ENVIRO-3000® Primer Sealer will seal most stains. If stain persists, a compatible stain blocker must be used. Wood knots should be spot primed with shellac. Pressure treated wood must be aged at least 6 months before priming.

SURFACE PREPARATION:

PREVIOUSLY PAINTED SURFACES:

Wash off all dirt, grease, soap and oil build-up with a powdered household cleaner and water. Rinse thoroughly. Remove loose paint and powdery substances. Patch cracks and holes with patching paste. Dull any nonporous or glossy surfaces by thorough washing with an abrasive kitchen cleaner or by scuff sanding. Rinse and/or remove any powdery residues. Spot prime patched areas before painting entire wall with ENVIRO-3000® Paint.

UNPAINTED SURFACES:

Drywall: Fill nail holes and cracks with patching paste. Remove all dirt and loose material. Spot prime patched areas before priming entire wall with ENVIRO-3000® Primer Sealer.

Plastered Walls: Surface must be dry, cured and hard. Textured or swirl types and soft, porous or powdery plaster must be treated with a solution of one pint household vinegar in one gallon of water. Repeat until surface is hard. Rinse with plain water. Let dry and apply a coat of ENVIRO-3000® Primer Sealer.

Non Ferrous Metal: Clean surface of all grease, oil and foreign matter before priming. Unprimed ferrous metals must be preprimed with METAL-PRIME RED-OX™, a Red Iron Oxide Primer Sealer.

Masonry: Prime masonry before painting. New masonry must either be sealed with CHALK-FORCE™ or aged 60 days before priming.

APPLICATION PROCEDURE:

Stir well before using. Thinning is not recommended but if necessary use water sparingly. Do not apply when temperatures are below 40 degrees Fahrenheit or when humidity is very high. Apply using brush, roller or spray. When rolling, apply in an "N" pattern first, then cross roll to spread paint, and finish with light roller strokes in downward direction. Always roll or brush from untouched into wet paint areas. Allow at least 4 hours to dry before applying the first coat of ENVIRO-3000™ paint.

CLEAN UP:

Clean up all spills, tools and overspray immediately while the coating is still wet with warm soapy water.

Ambient Temperature of 77°F and RH of 50% **TECHNICAL SPECIFICATIONS:** Rates & Times May Vary Beyond Specifications

FINISH:	Flat	SPREAD RATE:	250 to 400 sq.ft./gal.
COLOR:	White	DRY to TOUCH:	2 to 4 Hours
VEHICLE TYPE:	Copolymer Emulsion	RECOAT:	4 Hours
SOLIDS by WEIGHT:	55% +/- 2%	CURE TIME:	10 to 14 Days
SOLIDS by VOLUME:	35% +/- 2%	SIZES:	1 Gal., 5 Gal., 55 Gal.
V.O.C.'s (averages):	0 lbs./gal. • 0 g/liter	GALLON WEIGHT:	11.8 lbs. +/- .3 lbs.

Information presented on this Data Sheet has been compiled from sources to be reliable, and is accurate and reliable to the best of our knowledge and belief but is not guaranteed to be so.



MATERIALS HEALTH, SAFETY AND ENVIRONMENTAL DATA SHEET

MSDS#:
1090

Product Identification	<p>Product Name: ENVIRO-3000™ Primer Product Code #: 1090 General Usage: Interior Latex Primer General Description: Pigmented Latex Primer C.A.S. Number: None Established; Mixture</p>														
Manufacturer Information	<p>Manufacturer's Name: Nationwide Protective Coating Mfrs., Inc. Address: 7106 24th Court East; Sarasota, FL 34243-3993 Emergency Telephone: 1-800-423-7264 or 941-753-7500 Information: 1-800-423-7264 or 941-753-7500 Web Site: www.nationwidecoatings.com E-Mail: info@natcoat.net Date Effective: January 1st, 2005</p>														
Chemical and Physical Properties	<table style="width: 100%; border: none;"> <tr> <td style="width: 50%;">Color: White</td> <td style="width: 50%;">Odor: No Odor</td> </tr> <tr> <td>Physical State: Liquid</td> <td>Odor Threshold: Unknown</td> </tr> <tr> <td>Boiling Point: 212 Fahrenheit</td> <td>Melting Point: N/A</td> </tr> <tr> <td>Specific Gravity (H₂O=1): >1</td> <td>Freezing Point: 32 Fahrenheit</td> </tr> <tr> <td>Vapor Presence: about same as H₂O</td> <td>Solubility in H₂O: Soluble</td> </tr> <tr> <td>Percent Volatile: 43-53%</td> <td>pH (undiluted): 8 to 8.5</td> </tr> <tr> <td>Evaporation Rate (Butyl Acetate=1): <1</td> <td>Vapor Density (Air=1): <1</td> </tr> </table>	Color: White	Odor: No Odor	Physical State: Liquid	Odor Threshold: Unknown	Boiling Point: 212 Fahrenheit	Melting Point: N/A	Specific Gravity (H ₂ O=1): >1	Freezing Point: 32 Fahrenheit	Vapor Presence: about same as H ₂ O	Solubility in H ₂ O: Soluble	Percent Volatile: 43-53%	pH (undiluted): 8 to 8.5	Evaporation Rate (Butyl Acetate=1): <1	Vapor Density (Air=1): <1
Color: White	Odor: No Odor														
Physical State: Liquid	Odor Threshold: Unknown														
Boiling Point: 212 Fahrenheit	Melting Point: N/A														
Specific Gravity (H ₂ O=1): >1	Freezing Point: 32 Fahrenheit														
Vapor Presence: about same as H ₂ O	Solubility in H ₂ O: Soluble														
Percent Volatile: 43-53%	pH (undiluted): 8 to 8.5														
Evaporation Rate (Butyl Acetate=1): <1	Vapor Density (Air=1): <1														
Fire Protection Information	<table style="width: 100%; border: none;"> <tr> <td style="width: 50%;">Decomposition/Combustion:</td> <td style="width: 50%;">N/A</td> </tr> <tr> <td>Flash Point:</td> <td>N/A; Does Not Burn</td> </tr> <tr> <td>Recommended Extinguishing Media:</td> <td>N/A</td> </tr> <tr> <td>Flammable Limits:</td> <td>N/A</td> </tr> </table>	Decomposition/Combustion:	N/A	Flash Point:	N/A; Does Not Burn	Recommended Extinguishing Media:	N/A	Flammable Limits:	N/A						
Decomposition/Combustion:	N/A														
Flash Point:	N/A; Does Not Burn														
Recommended Extinguishing Media:	N/A														
Flammable Limits:	N/A														
Storage and Reactivity	<table style="width: 100%; border: none;"> <tr> <td style="width: 50%;">Hazardous Polymerization:</td> <td style="width: 50%;">Will Not Occur</td> </tr> <tr> <td>Storage Conditions:</td> <td>Keep from Freezing</td> </tr> <tr> <td>Toxic Products Which May Form:</td> <td>None</td> </tr> </table>	Hazardous Polymerization:	Will Not Occur	Storage Conditions:	Keep from Freezing	Toxic Products Which May Form:	None								
Hazardous Polymerization:	Will Not Occur														
Storage Conditions:	Keep from Freezing														
Toxic Products Which May Form:	None														
Transportation	<table style="width: 100%; border: none;"> <tr> <td style="width: 50%;">Hazard Classes:</td> <td style="width: 50%;">None; Not Hazardous</td> </tr> <tr> <td>Hazard Labels:</td> <td>Not Required</td> </tr> <tr> <td>Hazard Determination:</td> <td>MSD Sheet</td> </tr> <tr> <td>Shipping Containers:</td> <td>Varies</td> </tr> <tr> <td>Shipping Class:</td> <td>Class 55; Water Based Paint</td> </tr> </table>	Hazard Classes:	None; Not Hazardous	Hazard Labels:	Not Required	Hazard Determination:	MSD Sheet	Shipping Containers:	Varies	Shipping Class:	Class 55; Water Based Paint				
Hazard Classes:	None; Not Hazardous														
Hazard Labels:	Not Required														
Hazard Determination:	MSD Sheet														
Shipping Containers:	Varies														
Shipping Class:	Class 55; Water Based Paint														
Container Labeling	<p>Explanation of Unique Labeling System: None Used</p>														

Health Hazard Data	SHORT TERM EXPOSURE	
	Route of Entry: Inhalation: Skin: Eyes: Ingestion:	<p>Precautionary Treatment Expected None Expected None</p> <p>Flush Immediately with large amounts of water for at least 15 minutes, holding eyelids open. Call a physician if irritation persists</p> <p>Call a physician if significant amounts have been Swallowed. Give patient large amounts of water or milk for dilution.</p>
	LONG TERM EXPOSURE	
	Carcinogen: Target Organ Effects: Other Health Hazards:	<p>None None None Known</p>
Personal Protection	<p>Respiratory Protection: Protective Clothing: Ventilation: Other Protective Measures: Eye Protection:</p>	<p>No inhalation hazard expected Apron to keep off Clothes Local None Safety Glasses</p>
Spill or Leak Protection	<p>Accidental Release or Spill: Neutralizing Chemical/Media:</p>	<p>Collect liquid or solidify with absorbent package for disposal N/A</p>
Treatability	<p>Biodegradability: With water prior to cure. Influence on Biological Wastewater Treatment: None Other Impacts on Wastewater Treatment: None Recommended Wastewater Treatment: Dilutable Constituents Interfering With or Not Amenable to Biological or Wastewater Treatment: None</p>	
Recommended Waste Disposal	<p>Dispose of in accordance with Federal, State and Local guidelines.</p>	

EMERGENCY & INFO: 1-800-423-7264

Form based on O.S.H.A. Form 20. Information presented herein has been compiled from sources to be reliable and is accurate and reliable to be the best of our knowledge and belief but is not guaranteed to be so.

EMERGENCY & INFO: 941-753-7500