



**ELASTOMERIC ACRYLIC CERAMIC**  
**INSULKOTE™**  
**WATERPROOFING & INSULATING**  
**MATTE FINISH PROTECTIVE ROOF COATING**

 <b>8 YEAR</b> LIMITED MATERIAL WARRANTY	<b>PRODUCT DATA</b>
	<b>#7030</b>
	<b>10/01/25</b>
	<i>superseding: 03/27/13</i>

**PRODUCT DESCRIPTION:**

INSULKOTE™ is a Matte Finish, Bright White, Elastomeric Acrylic, Insulative and Reflective Ceramic, Waterproofing Protective ENERGY STAR® Roof Coating. It is a water-based, high build formula that possesses waterproofing, insulating and soundproofing properties that beautifies, protects and extends the life of most any sloped roofing surface. Forms a monolithic, thick rubber like ceramic shield of protection that expands and contracts with varying hot and cold temperatures, plus excellent resistance to thermal shock. INSULKOTE™ is an energy saving reflective coating that offers superior mildew resistance, ceramic insulation & soundproofing, excellent adhesion, U.V. ray reflectivity and a beautiful matte finish. An energy saving coating that combats the destructive environmental forces of nature. This easy to apply roof coating system will provide many years of durable protection and outstanding beauty, and will extend the roof's life. INSULKOTE™ is an inexpensive alternative solution to roofing and re-roofing. INSULKOTE™ offers an 8 YEAR LIMITED MATERIAL WARRANTY (see Warranty Compliance Information Section Below).

**INSULKOTE™ USES:**

Recommended for well draining, SLOPED roofing surfaces only (see Warranty Compliance Below). Excellent adhesion on weathered wood, shakes, plywood, clapboard, primed metal, galvanized, aluminum, tin, copper, asbestos, asphalt, urethane, polyester, primed styrofoam, weathered fiberglass, built-up-roofs, bonded roof gravel, rolled roofing, modified bitumen membranes, mineral surfaced roofing, concrete tiles, clay tiles, masonry tiles (flat or barrel), primed synthetic or aluminum, adobe, slate, slab, and various other substrates. INSULKOTE™ is ideal for residential, commercial and industrial applications. For flat roofs or limited ponding water situations inquire about PERMAKOTE PLUS®, Limited Ponding Water Roof Coating.

**SURFACE PREPARATION:**

Apply only to a sound, completely dry, well prepared roof surface. Leaks must be repaired before any coating is applied. An optional primer coat of ROOF-PRIME™, PERMABOND™ or METAL-PRIME RED-OX™ is recommended. If a primer was applied, it is essential that the primer surface is clean and dry and free of all moisture. If no primer was applied, prepare surface by thoroughly pressure washing with a water and chlorine mixture using at least 1500 P.S.I. to remove any previous coatings, dirt, grease, and other foreign materials, especially mold, mildew and algae. INSULKOTE™ will resist mildew growth, but will not kill mildew already on the surface. Patch any holes, cracks, flashings, valleys, vents, etc., with PERMAPATCH™, a Waterproof Caulk and Sealant. Tape & seal all seams with PERMATAPE™, a Polyester Fabric Tape.

**Metal:** Clean surface of all grease, oil and foreign matter before priming. Rusted metal and uncoated metal must be primed with METAL-PRIME RED-OX™, a Red Iron Oxide Primer Sealer. Use a degreaser on galvanized or coated metals which have oils or surface treatments. Check INSULKOTE™ adhesion on galvanized or coated metal by applying to a small area and evaluating after 48 hours. If lack of adhesion is present after evaluating, metal must be lightly scuffed without penetrating the coated finish or galvanizing. If applicable, use METAL-PRIME RED-OX™ to prime the penetrated areas.

**Fiberglass:** Fiberglass surfaces must be aged and weathered. New, smooth or shiny fiberglass will require sanding of the surface.

**APPLICATION PROCEDURE:**

Stir well before using. Do not thin, use product as is. Mix multiple containers of color together for greater color consistency. Do not apply when temperatures are below 45 degrees Fahrenheit or when humidity is very high. Do not apply when coating will be subjected to rain or heavy dew before it has had enough time to dry (approx. 2 to 4 hours). Drying time will vary depending on temperature, humidity and location. Apply using brush, roller or spray. Spread coating uniformly. Spread Rate will vary depending on surface. Apply each coat between 12 to 16 mils wet film thickness. Wait at least 12 hours before applying a second coat. Two coats resulting in a minimum 16 mil total dry film thickness is required and is mandatory for warranty compliance, or if the optional primer was used a minimum 20 mil total dry film thickness is required and is mandatory for warranty compliance.

**Airless Sprayers:** Use at least a 1 gallon per minute piston type airless sprayer with a recommended tip size of .025. Remove all line filters and gun filters before spraying.

**Clean Up:** Clean up all spills, tools and overspray immediately while the coating is still wet with warm soapy water.

**WARRANTY COMPLIANCE INFORMATION:**

*The INSULKOTE™ 8 YEAR LIMITED MATERIAL WARRANTY is for Product Only and applies to chipping, cracking and peeling, only. Labor is not covered by this warranty. This product is not guaranteed to stop or prevent leaks; all leaks must be repaired prior to the application of any coating. The WARRANTY is available only when product is applied according to Manufacturer's Application Procedures and Strict Material Requirement Specifications and a Warranty Registration (and a Job Completion Form if coated area exceeds 10,000 square feet) is submitted to Manufacturer within 90 days of completed coating application date (Application Procedure Sheets available upon request).*

**SLOPED ROOFS ONLY:** This Warranty is available for well draining, sloped roofing surfaces only. Slope of roof must be greater than 1" per 24" or an angle greater than 4 degrees, otherwise inquire about PERMAKOTE PLUS® Limited Ponding Water Roof Coating for Flat Roofing Surfaces.

**MIL THICKNESS:** Primer is optional but recommended. Use either ROOF-PRIME™, PERMABOND™ or METAL-PRIME depending on roof condition. The primer coat and two coats of INSULKOTE™ must result in a minimum 20 mil total dry film thickness. If primer was not used, two coats of INSULKOTE™ must result in a minimum 16 mil total dry film thickness.

**MINIMUM SPREAD RATES:** If optional primer coat was used, PRIMER must be applied at no more than 150 square feet per gallon. INSULKOTE™ must be applied at no more than 150 square feet per gallon per coat, resulting in an aggregate spread rate of 75 square feet per gallon for both coats.

<b>TECHNICAL SPECIFICATIONS:</b>		Rates & Times May Vary Beyond Specifications	
Ambient Temperature of 77°F and RH of 50%			
FINISH:	Matte	SPREAD RATE:	100 - 150 sq.ft. per gallon
COLOR:	White, Deep & Clear Base	DRY to TOUCH:	2 to 4 Hours
VEHICLE TYPE:	Copolymer Emulsion	RECOAT:	12 Hours
SOLIDS by WEIGHT:	61% +/- 2%	CURE TIME:	5 to 7 Days
SOLIDS by VOLUME:	44% +/- 2%	SIZES:	1 Gal., 5 Gal., 55 Gal.
V.O.C.'s (averages):	.33 lbs./gal. • 40.0 g/liter	GALLON WEIGHT:	11.9 lbs. +/- .3 lbs.

*Information presented on this Data Sheet has been compiled from sources to be reliable, and is accurate and reliable to the best of our knowledge and belief but is not guaranteed to be so.*

*In Any Event Nationwide Protective Coating Manufacturers, Inc. will not be liable or responsible for any past, present or future leaks or any resulting consequential or incidental damages.*



# MATERIALS HEALTH, SAFETY AND ENVIRONMENTAL DATA SHEET

**MSDS#:  
7030**

<b>Product Identification</b>	Product Name: <b>INSULKOTE™</b> Product Code #: <b>7030</b> General Usage: Exterior Latex Roof Coating General Description: Pigmented Latex Coating C.A.S. Number: None Established; Mixture														
<b>Manufacturer Information</b>	Manufacturer's Name: Nationwide Protective Coating Mfrs., Inc. Address: 7106 24th Court East; Sarasota, FL 34243-3993 Emergency Telephone: 1-800-423-7264 or 941-753-7500 Information: 1-800-423-7264 or 941-753-7500 Web Site: www.nationwidecoatings.com E-Mail: info@natcoat.net Date Effective: January 1 <sup>st</sup> , 2015														
<b>Chemical and Physical Properties</b>	<table style="width: 100%; border: none;"> <tr> <td style="width: 50%;">Color: White</td> <td style="width: 50%;">Odor: Pungent Odor</td> </tr> <tr> <td>Physical State: Liquid</td> <td>Odor Threshold: Unknown</td> </tr> <tr> <td>Boiling Point: 212 Fahrenheit</td> <td>Melting Point: N/A</td> </tr> <tr> <td>Specific Gravity (H<sub>2</sub>O=1): &gt;1</td> <td>Freezing Point: 32 Fahrenheit</td> </tr> <tr> <td>Vapor Presence: about same as H<sub>2</sub>O</td> <td>Solubility in H<sub>2</sub>O: Soluble</td> </tr> <tr> <td>Percent Volatile: 33-38%</td> <td>pH (undiluted): 8 to 8.5</td> </tr> <tr> <td>Evaporation Rate (Butyl Acetate=1): &lt;1</td> <td>Vapor Density (Air=1): &lt;1</td> </tr> </table>	Color: White	Odor: Pungent Odor	Physical State: Liquid	Odor Threshold: Unknown	Boiling Point: 212 Fahrenheit	Melting Point: N/A	Specific Gravity (H <sub>2</sub> O=1): >1	Freezing Point: 32 Fahrenheit	Vapor Presence: about same as H <sub>2</sub> O	Solubility in H <sub>2</sub> O: Soluble	Percent Volatile: 33-38%	pH (undiluted): 8 to 8.5	Evaporation Rate (Butyl Acetate=1): <1	Vapor Density (Air=1): <1
Color: White	Odor: Pungent Odor														
Physical State: Liquid	Odor Threshold: Unknown														
Boiling Point: 212 Fahrenheit	Melting Point: N/A														
Specific Gravity (H <sub>2</sub> O=1): >1	Freezing Point: 32 Fahrenheit														
Vapor Presence: about same as H <sub>2</sub> O	Solubility in H <sub>2</sub> O: Soluble														
Percent Volatile: 33-38%	pH (undiluted): 8 to 8.5														
Evaporation Rate (Butyl Acetate=1): <1	Vapor Density (Air=1): <1														
<b>Fire Protection Information</b>	<table style="width: 100%; border: none;"> <tr> <td style="width: 50%;">Decomposition/Combustion:</td> <td style="width: 50%;">N/A</td> </tr> <tr> <td>Flash Point:</td> <td>N/A; Does Not Burn</td> </tr> <tr> <td>Recommended Extinguishing Media:</td> <td>N/A</td> </tr> <tr> <td>Flammable Limits:</td> <td>N/A</td> </tr> </table>	Decomposition/Combustion:	N/A	Flash Point:	N/A; Does Not Burn	Recommended Extinguishing Media:	N/A	Flammable Limits:	N/A						
Decomposition/Combustion:	N/A														
Flash Point:	N/A; Does Not Burn														
Recommended Extinguishing Media:	N/A														
Flammable Limits:	N/A														
<b>Storage and Reactivity</b>	<table style="width: 100%; border: none;"> <tr> <td style="width: 50%;">Hazardous Polymerization:</td> <td style="width: 50%;">Will Not Occur</td> </tr> <tr> <td>Storage Conditions:</td> <td>Keep from Freezing</td> </tr> <tr> <td>Toxic Products Which May Form:</td> <td>None</td> </tr> </table>	Hazardous Polymerization:	Will Not Occur	Storage Conditions:	Keep from Freezing	Toxic Products Which May Form:	None								
Hazardous Polymerization:	Will Not Occur														
Storage Conditions:	Keep from Freezing														
Toxic Products Which May Form:	None														
<b>Transportation</b>	<table style="width: 100%; border: none;"> <tr> <td style="width: 50%;">Hazard Classes:</td> <td style="width: 50%;">None; Not Hazardous</td> </tr> <tr> <td>Hazard Labels:</td> <td>Not Required</td> </tr> <tr> <td>Hazard Determination:</td> <td>MSD Sheet</td> </tr> <tr> <td>Shipping Containers:</td> <td>Varies</td> </tr> <tr> <td>Shipping Class:</td> <td>Class 55; Water Based Paint</td> </tr> </table>	Hazard Classes:	None; Not Hazardous	Hazard Labels:	Not Required	Hazard Determination:	MSD Sheet	Shipping Containers:	Varies	Shipping Class:	Class 55; Water Based Paint				
Hazard Classes:	None; Not Hazardous														
Hazard Labels:	Not Required														
Hazard Determination:	MSD Sheet														
Shipping Containers:	Varies														
Shipping Class:	Class 55; Water Based Paint														
<b>Container Labeling</b>	Explanation of Unique Labeling System: None Used														

<b>Health Hazard Data</b>	SHORT TERM EXPOSURE	
	Route of Entry: Inhalation: Skin:  Eyes:  Ingestion:	Precautionary Treatment Expected None Expected None  Flush Immediately with large amounts of water for at least 15 minutes, holding eyelids open. Call a physician if irritation persists  Call a physician if significant amounts have been Swallowed. Give patient large amounts of water or milk for dilution.
	LONG TERM EXPOSURE	
	Carcinogen: Target Organ Effects: Other Health Hazards:	None None None Known
<b>Personal Protection</b>	Respiratory Protection: Protective Clothing: Ventilation: Other Protective Measures: Eye Protection:	No inhalation hazard expected None Required Local None Safety Glasses
<b>Spill or Leak Protection</b>	Accidental Release or Spill:  Neutralizing Chemical/Media:	Collect liquid or solidify with absorbent package for disposal  N/A
<b>Treatability</b>	Biodegradability: With water prior to cure. Influence on Biological Wastewater Treatment: None Other Impacts on Wastewater Treatment: None Recommended Wastewater Treatment: Dilutable Constituents Interfering With or Not Amenable to Biological or Wastewater Treatment: None	
<b>Recommended Waste Disposal</b>	Dispose of in accordance with Federal, State and Local guidelines.	

**EMERGENCY & INFO: 1-800-423-7264**

*Form based on O.S.H.A. Form 20. Information presented herein has been compiled from sources to be reliable and is accurate and reliable to be the best of our knowledge and belief but is not guaranteed to be so.*

**EMERGENCY & INFO: 941-753-7500**