



ELASTOMERIC ACRYLIC CERAMIC
ULTRA SEAL™
WATERPROOFING & INSULATING
MATTE FINISH PROTECTIVE WALL COATING

PRODUCT DATA
#2725
25 YEAR*
LIMITED MATERIAL WARRANTY
02/15/19
*10 Years on Roofs
superseding: 03/03/16

PRODUCT DESCRIPTION:

ULTRA SEAL™ is a bright white, matte finish, elastomeric acrylic, insulating ceramic, Protective Waterproofing Wall Coating and **ENERGY STAR®** Roof Coating. An elastomeric acrylic, latex based, high build formula that provides waterproofing, insulating, and soundproofing performance in a beautiful protective finish. Innovative elastomeric resin technology results in an extremely durable, waterproofing elastic film that has excellent resistance to thermal shock by expanding and contracting with hot and cold temperatures, but also has good impact resistance and excellent chemical resistance. A self-priming coating that forms a thick rubber like ceramic shield of protection that actually becomes part of the substrate due to excellent adhesion and bonding. **ULTRA SEAL™** offers superior mildew resistance, corrosion resistance, scratch and mar resistance, ceramic insulation & soundproofing, excellent adhesion, ultraviolet ray reflectivity and a beautiful matte finish. Excellent anti-carbonation protection on concrete substrates. **ULTRA SEAL™** passed the CLASS A Fire Rating Test ASTM E84-01 as per NFPA 101 Life Safety Code. Originally designed as a Commercial Coating for hi-rises, multi-story buildings and skyscrapers to reduce costly maintenance, repairs and frequent repainting, and is now also used as an insulating, energy saving, wall coating that stabilizes, strengthens and protects while combating the destructive environmental forces of nature. This easy to apply coating system will provide many years of durable protection and outstanding beauty. Available in a beautiful Satin Finish also; inquire about **ULTRA SATIN™**. A TWENTY FIVE YEAR LIMITED MATERIAL WARRANTY is available when product is applied according to Manufacturer's Specifications and a Warranty Registration is completed and approved within 90 days of application date (see Warranty Compliance Information Section Below).

PRODUCT USES:

Excellent adhesion on most any interior or exterior surface including: weathered wood, shakes, plywood, clapboard, primed metal, galvanized, primed synthetic or aluminum siding, aluminum, tin, copper, asbestos, asphalt, urethane, polyester, primed Styrofoam, adobe, brick, stucco, concrete, clay, masonry, slate, slab and various other substrates. For residential, commercial & industrial applications.
Roofs: Recommended for well draining, SLOPED roofing surfaces only (see Warranty Compliance Information Section Below).

SURFACE PREPARATION:

Trenching is necessary to form a complete seal. If applicable, trench 4 to 6 inches around the perimeter of the structure. Prepare Exterior Surfaces by thoroughly pressure washing with a water and chlorine solution (unless previously done before primer coat) using at least 1500 P.S.I. to remove any previous coatings, dirt, grease, and other foreign materials, especially mold, mildew and algae. **ULTRA SEAL™** will resist mildew growth, but will not kill mildew already on the surface. Clean Interior Surfaces by washing off all dirt, grease, soap and oil build-up with a powdered household cleaner and water. Rinse thoroughly. Remove loose paint and powdery substances. If after cleaning, there is still chalk present or existing coating is compromised, apply a coat of **ULTRA PRIME™** Primer Sealer before the application of **ULTRA SEAL™**. Patch any holes, cracks, seams, imperfections, etc., with **PERMAPATCH™**, Waterproofing Caulk & Sealant.

Metal: Clean surface of all grease, oil and foreign matter before priming. Rusted metal and uncoated metal must be primed with **METAL-PRIME RED-OX™**, a Red Iron Oxide Primer Sealer. Use a degreaser on galvanized or coated metals which have oils or surface treatments. Check **ULTRA SEAL™** adhesion on galvanized or coated metal by applying to a small area and evaluating after 48 hours. If lack of adhesion is present after evaluating, metal must be lightly scuffed without penetrating the coated finish or galvanizing. If applicable, use **METAL-PRIME RED-OX™** to spot prime the penetrated areas, then use **ULTRA PRIME™** Primer for entire coated or galvanized surface.

APPLICATION PROCEDURE:

Stir well before using. Do not thin, use product as is. Do not apply when temperatures are below 45 degrees Fahrenheit or when humidity is very high. Do not apply when coating will be subjected to rain or heavy dew before it has had enough time to dry (approx. 2 to 4 hours). Drying time will vary depending on temperature, humidity and location. Apply using brush, roller or spray. Spread coating uniformly. Spread Rate may vary depending on surface. Apply each coat between 12 to 16 mils wet film thickness. Wait at least 12 hours before applying a second coat. Two coats resulting in a minimum 16 mil total dry film thickness are required for the TWENTY FIVE YEAR LIMITED MATERIAL WARRANTY.

Airless Sprayers: Use at least a 1 gallon per minute piston type airless sprayer with a minimum tip size of .025. Remove all line filters and gun filters before spraying.

Clean Up: Clean up all spills, tools and overspray immediately while the coating is still wet with warm soapy water.

WARRANTY COMPLIANCE INFORMATION:

The **ULTRA SEAL™** 25 YEAR LIMITED MATERIAL WARRANTY (Roofs 10 Years / All Other 25 Years) is for Product Only and applies to chipping, cracking and peeling, only. Labor is not covered by this warranty. This product is not guaranteed to stop or prevent leaks; all leaks must be repaired prior to the application of any coating. The WARRANTY is available only when product is applied according to Manufacturer's Application Procedures and Strict Material Requirement Specifications and a Warranty Registration (and a Job Completion Form if coated area exceeds 10,000 square feet) is submitted to Manufacturer within 90 days of completed coating application date (Application Procedure Sheets available upon request).

The **ULTRA SEAL™** roof application is for WELL DRAINING, SLOPED ROOFING SURFACES ONLY and requires a PRIMER COAT of **PERMABOND™** or **METAL-PRIME RED-OX™**. Slope of roof must be greater than 1" per 24" or an angle greater than 4 degrees, otherwise inquire about **PERMAKOTE PLUS®** Limited Ponding Water Roof Coating for Flat Roofing Surfaces.

MIL THICKNESS: Primer is optional but recommended (primer is required on roof applications). Use either **ULTRA PRIME™** for Walls, **PERMABOND™** for Roofs or **METAL-PRIME RED-OX™** for exposed or unprimed Metal. The primer coat and two coats of **ULTRA SEAL™** must result in a minimum 20 mil total dry film thickness. If primer was not used, two coats of **ULTRA SEAL™** must result in a minimum 16 mil total dry film thickness.

Ambient Temperature of 77°F and RH of 50% **TECHNICAL SPECIFICATIONS:** Rates & Times May Vary Beyond Specifications

FINISH:	Matte	SPREAD RATE:	100 to 175 sq.ft./gal.
COLOR:	White, Deep & Clear Base	DRY to TOUCH:	2 to 4 Hours
VEHICLE TYPE:	Copolymer Emulsion	RECOAT:	12 Hours
SOLIDS by WEIGHT:	59% +/- 2%	CURE TIME:	5 to 7 Days
SOLIDS by VOLUME:	47% +/- 2%	SIZES:	1 Gal., 5 Gal., 55 Gal.
V.O.C.'s (averages):	.38 lbs./gal. • 45.0 g/liter	GALLON WEIGHT:	11.2 lbs. +/- .3 lbs.

Information presented on this Data Sheet has been compiled from sources to be reliable, and is accurate and reliable to the best of our knowledge and belief but is not guaranteed to be so.

In Any Event Nationwide Protective Coating Manufacturers, Inc. will not be liable or responsible for any past, present or future leaks or any resulting consequential or incidental damages.



MATERIALS HEALTH, SAFETY AND ENVIRONMENTAL DATA SHEET

**MSDS#:
2725**

Product Identification	Product Name: ULTRA SEAL™ Product Code #: 2725 General Usage: Exterior Latex Elastomeric Wall Coating General Description: Pigmented Latex Coating C.A.S. Number: None Established; Mixture	
Manufacturer Information	Manufacturer's Name: Nationwide Protective Coating Mfrs., Inc. Address: 7106 24th Court East; Sarasota, FL 34243-3993 Emergency Telephone: 1-800-423-7264 or 941-753-7500 Information: 1-800-423-7264 or 941-753-7500 Web Site: www.nationwidecoatings.com E-Mail: info@natcoat.net Date Effective: January 1 st , 2005	
Chemical and Physical Properties	Color: White Physical State: Liquid Boiling Point: 212 Fahrenheit Specific Gravity (H ₂ O=1): >1 Vapor Presence: about same as H ₂ O Percent Volatile: 30-35% Evaporation Rate (Butyl Acetate=1): <1	Odor: Pungent Odor Odor Threshold: Unknown Melting Point: N/A Freezing Point: 32 Fahrenheit Solubility in H ₂ O: Soluble pH (undiluted): 8 to 8.5 Vapor Density (Air=1): <1
Ingredients C.A.S. Numbers	Modified Acrylic Polymer Titanium Dioxide Calcium Carbonate Zinc Borate Barium Sulfate Ethylene Glycol Ammonia Trimethyl Pentandiol Monoisobutyrate Mineral Spirits Ceramic Micro Spheres	Proprietary (non-hazardous) C.A.S. #: 13463-67-7 C.A.S. #: 1317-65-3 C.A.S. #: 138265-88-0 C.A.S. #: 7727-43-7 C.A.S. #: 107-21-1 C.A.S. #: 7664-41-7 C.A.S. #: 25265-77-4 C.A.S. #: 8052-41-3 C.A.S. #: 66402-68-4
Fire Protection Information	Decomposition/Combustion: Flash Point: Recommended Extinguishing Media: Flammable Limits:	N/A N/A; Does Not Burn N/A N/A
Storage and Reactivity	Hazardous Polymerization: Storage Conditions: Toxic Products Which May Form:	Will Not Occur Keep from Freezing None
Transportation	Hazard Classes: Hazard Labels: Hazard Determination: Shipping Containers: Shipping Class:	None; Not Hazardous Not Required MSD Sheet Varies Class 55; Water Based Paint

Health Hazard Data	SHORT TERM EXPOSURE	
	Route of Entry: Inhalation: Skin: Eyes: Ingestion:	Precautionary Treatment Expected None Expected None Flush Immediately with large amounts of water for at least 15 minutes, holding eyelids open. Call a physician if irritation persists Call a physician if significant amounts have been Swallowed. Give patient large amounts of water or milk for dilution.
Personal Protection	LONG TERM EXPOSURE	
	Carcinogen: Target Organ Effects: Other Health Hazards:	None None None Known
Spill or Leak Protection	Respiratory Protection: Protective Clothing: Ventilation: Other Protective Measures: Eye Protection:	No inhalation hazard expected None Required Local None Safety Glasses
Treatability	Accidental Release or Spill: Neutralizing Chemical/Media:	Collect liquid or solidify with absorbent package for disposal N/A
Labeling	Biodegradability: With water prior to cure. Influence on Biological Wastewater Treatment: None Other Impacts on Wastewater Treatment: None Recommended Wastewater Treatment: Dilutable Constituents Interfering With or Not Amenable to Biological or Wastewater Treatment: None	
Waste Disposal	Explanation of Unique Labeling System: None Used Dispose of in accordance with Federal, State and Local guidelines.	

EMERGENCY & INFO: 1-800-423-7264

Form based on O.S.H.A. Form 20. Information presented herein has been compiled from sources to be reliable and is accurate and reliable to be the best of our knowledge and belief but is not guaranteed to be so.

EMERGENCY & INFO: 941-753-7500